

# KCR2(E) Multi-end Roving



## MULTI-END ROVING FOR SPRAY-UP PROCESS

### Product Description:

KCR2(E) multi-end roving offers solutions for spray-up applications, due to its easy choppability and fast wet-out properties.





### Features and Benefits:

- Manufacturing in accordance with ISO 9001:2015 conditions
- Good unwinding
- Very good choppability and uniform fiber dispersion
- Very low static load
- Fast wet-out
- Low resin consumption
- Very low fuzz generation during processing

### Product Specifications:

<b>Glass Type</b>	E	<b>Sizing Content (%)</b>	0.90 ± 0.15
<b>Tex (g/1000 m)</b>	2400 ± 5%	<b>Split Tex (g/1000 m)</b>	Nom. 60
<b>Fiber Diameter (μ)</b>	Nom. 14	<b>Moisture Content (%)</b>	max. 0.1
<b>Sizing Type</b>	Silane	<b>Resin Compatibility</b>	Unsaturated Polyester, Vinylester

### End-use Markets:

-  Bathroom Equipments
-  Marine
-  Automotive
-  Sports and Leisure

### Bobbin Dimensions:

Inner Diameter (mm): 100  
External Diameter (mm): 300  
Height (mm): 260  
Weigth (kg): 23

### Packing Information:

<b>Packaging</b>	With / Without Paper Body
<b>Number of Layers per Pallet</b>	4
<b>Number of Bobbins per Layer</b>	12
<b>Number of Bobbins per Pallet</b>	48
<b>Pallet Dimensions (cm)</b>	95 x 125
<b>Pallet Height (cm)</b>	125
<b>Average Pallet Net Weight (kg)</b>	1000
<b>Number of Ends</b>	0-1-2-3-4



Please scan the QR code for more detailed packaging information.

### Storage Conditions:

Product should be stored in dry area at room temperature and relative humidity of approx 65%. Product should be conditioned for 24 hours in the work area prior to use. In case of partial usage, package should be re-sealed.

Form No: EN-3117-1

Revision Date: 03.2023