



KİMYASAL ÖZELLİKLERİ (%):

SiO ₂	68,00 ± 2,00
Al ₂ O ₃	18,50 ± 0,50
TiO ₂	0,550 max.
Fe ₂ O ₃	0,600 max.
CaO	0,60 ± 0,15
MgO	1,20 ± 0,50
Na ₂ O	9,50 ± 0,50
K ₂ O	0,60
P ₂ O ₅	0,18 ± 0,06
L.O.I	0,60 ± 0,15

TANE BOYUTU (%):

d98	< 10 mm
d85	
+ 500 µ	
-500, + 300 µ	
- 74 µ	

MİNEROLOJİK ÖZELLİKLER (%):

Albit	
Ortoklas	
Kuvars	
Anortit	
L	
a	
b	

RUTUBET (%):

8 max.

AMBALAJ:

Dökme