



KİMYASAL ÖZELLİKLERİ (%):

SiO ₂	70,00 ± 3,00
Al ₂ O ₃	18,50 ± 1,00
TiO ₂	0,320 max.
Fe ₂ O ₃	0,27 ± 0,05
CaO	0,80 ± 0,50
MgO	0,4 ± 0,10
Na ₂ O	9,70 ± 0,40
K ₂ O	0,5 ± 0,20
P ₂ O ₅	0,15 ± 0,10
L.O.I	0,50 ± 0,15

TANE BOYUTU (%):

d98	< 10 mm
d85	
+500 µ	
-500 +300 µ	
-74 µ	

MİNEROLOJİK ÖZELLİKLER (%):

Albit	75-80
Ortoklas	2-4
Kuvars	12-20
Anortit	5-6
L	75 ± 3
a	4,5 ± 1
b	25 ± 2

RUTUBET (%):

6,0 max.

AMBALAJ:

Dökme

ŞİŞECAM KİMYASALLAR



CHEMICAL CONTENT (%):

SiO ₂	70,00 ± 3,00
Al ₂ O ₃	18,50 ± 1,00
TiO ₂	0,320 max.
Fe ₂ O ₃	0,27 ± 0,05
CaO	0,80 ± 0,50
MgO	0,4 ± 0,10
Na ₂ O	9,70 ± 0,40
K ₂ O	0,5 ± 0,20
P ₂ O ₅	0,15 ± 0,10
L.O.I	0,50 ± 0,15

PARTICLE SIZE (%):

d98	< 10 mm
d85	
+500 µ	
-500 +300 µ	
-74 µ	

MINERALOGY (%):

Albite	75-80
Orthoclase	2-4
Quartz	12-20
Anortithe	5-6
L	75 ± 3
a	4,5 ± 1
b	25 ± 2

MOISTURE (%):

6,0 max.

PACKING:

Bulk

ŞİŞECAM CHEMICALS